

# KILN DRIED SOUTHERN YELLOW PINE

(Primarily Longleaf Pine)

## PRIME & BETTER GRADE SPECIFICATION 4/4 AND 5/4

**MAX WANE:** Depth; ½ edge – width; 1" wide across the face - length; 2' long.

**KNOTS:** Must be well spaced. No loose knots allowed. No edge knots.

- 1X4 and 1X6 - 2 knots max - ¾" on face & 1" backside
- 1X8, 1X10 and 1X12 – 2 knots max - 1" on face & 1-1/2" backside

**PITCH POCKETS:** Same as knots.

**HOLE:** None allowed.

**BLUE STAIN:** None allowed.

**MOLD:** None allowed.

**SHAKES:** None allowed.

**MOISTURE CONTENT:** 15% and below.

# KILN DRIED NORTHERN RED OAK

## THERMAL MODIFICATION GRADE 4/4 AND 5/4

- S2S Hit & Miss
- Parallel-sawn to full width after KD
- 6' and longer as develops

### Questions?

Please visit [www.klaaswood.com](http://www.klaaswood.com) for more information.

# KWD